



- HIGH HARDNESS
- TWO COMPONENT
- FOOT TRAFFIC
- STAIN RESISTANT
- HIGH ADHESION
- COLOUR OPTIONS
- SEAMLESS FINISH
- EXCELLENT WORKABILITY

MICREX RUSTIK

HIGH-HARDNESS EPOXY
MICROCEMENT · TEXTURED

MICROSTONE®
BY MICROFORCE

DESCRIPTION

Micrex Rustik is a high-hardness, three-component epoxy microcement made with water-based resins and fine aggregate. It gives coloured floors and walls a hand-trowelled, textured finish with outstanding mechanical and abrasion resistance — and it is UV and weather resistant, so it works outside too.

KEY FEATURES

- High-hardness epoxy microcement
- Decorative trowelled (spatulated) finish
- Excellent mechanical strength and abrasion resistance
- Excellent UV and weather resistance
- Floors and walls, interior and exterior

TECHNICAL INFORMATION

PRODUCT TYPE

Three-component water-based epoxy microcement (A+B+C)

MIXING RATIO

A 100 : B 50 : C 100 by weight

CONSUMPTION

0.3–1.0 kg/m² per coat, depending on aggregate

POT LIFE (25°C)

> 2 hours

TOUCH DRY (25°C)

8–10 hours

FOOT TRAFFIC

> 24 hours (25°C)

ADHESION TO CONCRETE

> 2 N/mm²

DENSITY

1.80 ± 0.05 g/ml



HOW IT'S APPLIED

- 1 Prepare** — concrete sound, dry, level and absorbent, cured >28 days, minimum 25 N/mm² compressive and 15 N/mm² tensile strength.
- 2 Base** — apply Micrex Base.
- 3 Mix** — pour B into A, mix, add C, then homogenise at low speed.
- 4 Apply** — steel trowel at approx. 0.3–0.5 kg/m² per coat.

COVERAGE

Approximately
25–83m²
per coat per 25 kg pack
(depending on aggregate)

APPLICATION



MIXER



TROWEL



SEAL

PACKAGING



25KG
Pack A+B+C



PROFESSIONAL PERFORMANCE

Engineered for strength, adhesion and durability.



LOW VOC

Safe for installers and the environment.



WATERPROOF

Reliable protection in wet areas.



PREMIUM QUALITY

Developed for the most demanding projects.

MICROSTONE®

BY MICROFORCE

microstone.co.uk